

In the Claims:

Please amend the claims by deleting the text shown as strikethrough and adding the text shown in underline.

1. (Currently amended) A method of regenerating a reactor, comprising forming
~~characterized in that~~ ammonium salts ~~formed~~ as by-product in the reactor in a ~~are brought into~~
~~the~~ gas phase at temperatures of $\geq 150^{\circ}\text{C}$ and taking the ammonium salts ~~taken~~ from the reactor
in gaseous form.

2. (Currently amended) A process for preparing a product, in which ammonium salt is
formed as by-product, comprising bringing ammonium salts formed as by-product ~~characterized~~
~~in that~~ a regeneration step ~~in which ammonium salts formed as by-product are brought into the~~
gas phase at temperatures of $\geq 150^{\circ}\text{C}$.

3. (Currently amended) The process as claimed in claim 2, wherein ~~characterized in that~~
the ammonium salts which have been brought into the gas phase are separated off.

4. (Currently amended) The process as claimed in claim 2, wherein ~~either of claims 2 and~~
~~3, characterized in that~~ the product is a single-component precursor of nonoxidic ceramics.

5. (Currently amended) The process as claimed in claim 4, wherein ~~characterized in that~~
the product is a compound which has the structural feature X-N-Y, where X and Y can each be,
independently of one another, Si, P, Al, Ti, V, Zr, B, Ga or/and In.

6. (Currently amended) The process as claimed in claim 5, wherein ~~any of claims 2 to 5,~~
~~characterized in that~~ the compound has the formula (I) $\text{R}_x\text{Hal}_{3-x}\text{Si-NR}^1\text{-BR}_y\text{Hal}_{2-y}$,

where the radicals Hal are each, independently of one another, Cl, Br or I,
the radicals R are each, independently of one another, a hydrocarbon radical having from
1 to 20 carbon atoms or hydrogen,
 R^1 is a hydrocarbon radical having from 1 to 20 carbon atoms or hydrogen,
x is 0, 1 or 2 and

y is 0 or 1.

7. (Currently amended) The process as claimed in claim 4, wherein any of claims 2 to 4,
~~characterized in that~~ the synthesis of the product, in particular a single-component precursor, is
carried out in a two-stage reaction process, in particular in the gas phase.

8. (Currently amended) The process as claimed in claim 4, wherein any of claims 2 to 7,
~~characterized in that~~ the process further comprises the steps

(i) synthesizing ~~synthesis of~~ a product, in particular a single-component precursor of
nonoxidic ceramics having a nitrogen bridging function, in a two-stage reaction, in
particular in the gas phase and

(ii) regenerating ~~regeneration of~~ the reactor by heating to temperatures of $\geq 150^{\circ}\text{C}$.

9. (Currently amended) The process as claimed in claim 8, wherein any of claims 2 to 8,
~~characterized in that~~ the synthesis phase and the regeneration phase are carried out alternatively a
plurality of times and, in particular, are carried out cyclically in succession.

10. (Currently amended) The process as claimed in claim 8, wherein any of claims 2 to 9,
~~characterized in that~~ the switching over between the synthesis phase and the regeneration phase is
controlled by the total pressure drop in the reaction steps.

11. (Currently amended) The process as claimed in claim 8, wherein any of claims 2 to 10,
~~characterized in that~~ the change between synthesis ~~production~~ phase and regeneration phase is
controlled by a temperature change.

12. (Currently amended) A pseudocontinuous process for preparing a product, in which an
ammonium salt is formed as by-product and the preparation is carried out in a two-stage reaction,
comprising using ~~characterized in that~~ two apparatuses ~~are used~~ per reaction stage, of which one

is operated in the production mode and the other is operated in the regeneration mode, ~~i.e.~~ at temperatures of $\geq 150^{\circ}\text{C}$.

13. (Currently amended) The process as claimed in claim 12, wherein any of the preceding claims, characterized in that the product is isolated from the remaining components of the reaction mixture, in particular by crystallization, condensation and/or the use of a solvent.

14. (Currently amended) The process as claimed in claim 12, wherein any of claims 2 to 13, characterized in that unreacted starting materials are recycled.

15. (Currently amended) The process as claimed in claim 12, wherein any of claims 1 to 14, characterized in that MeNH_2 and at least one of the compounds SiCl_4 , BCl_3 , PCl_3 , PCl_5 , AlCl_3 , GaCl_3 , InCl_3 , TiCl_4 , VCl_3 , VCl_4 , ZrCl_4 or TaCl_5 are used as starting materials for the first reaction step.

16. (Currently amended) The process as claimed in claim 12, wherein any of claims 1 to 15, characterized in that the intermediate product from the first reaction step and at least one of the compounds SiCl_4 , BCl_3 , PCl_3 , PCl_5 , AlCl_3 , GaCl_3 , InCl_3 , TiCl_4 , VCl_3 , VCl_4 , ZrCl_4 or TaCl_5 are used as starting materials for the second reaction step.

17. (New) The process as claimed in claim 2, wherein the product is isolated from the remaining components of the reaction mixture, in particular by crystallization, condensation and/or the use of a solvent.

18. (New) The process as claimed in claim 1, wherein unreacted starting materials are recycled.

19. (New) The process as claimed in claim 2, wherein unreacted starting materials are recycled.

20. (New) The process as claimed in claim 1, wherein MeNH_2 and at least one of the compounds SiCl_4 , BCl_3 , PCl_3 , PCl_5 , AlCl_3 , GaCl_3 , InCl_3 , TiCl_4 , VCl_3 , VCl_4 , ZrCl_4 or TaCl_5 are used as starting materials for the first reaction step.


21. (New) The process as claimed in claim 2, wherein MeNH_2 and at least one of the compounds SiCl_4 , BCl_3 , PCl_3 , PCl_5 , AlCl_3 , GaCl_3 , InCl_3 , TiCl_4 , VCl_3 , VCl_4 , ZrCl_4 or TaCl_5 are used as starting materials for the first reaction step.

22. (New) The process as claimed in claim 1, wherein the intermediate product from the first reaction step and at least one of the compounds SiCl_4 , BCl_3 , PCl_3 , PCl_5 , AlCl_3 , GaCl_3 , InCl_3 , TiCl_4 , VCl_3 , VCl_4 , ZrCl_4 or TaCl_5 are used as starting materials for the second reaction step.

23. (New) The process as claimed in claim 2, wherein the intermediate product from the first reaction step and at least one of the compounds SiCl_4 , BCl_3 , PCl_3 , PCl_5 , AlCl_3 , GaCl_3 , InCl_3 , TiCl_4 , VCl_3 , VCl_4 , ZrCl_4 or TaCl_5 are used as starting materials for the second reaction step.

No new matter is presented in the priority amendments to the specification and clarifying amendments to the claims. No fees are believed to be due, however, should there be any fees associated with this filing, the Commissioner is hereby authorized to charge Deposit Account No. 19-5029. A duplicate copy of this transmittal is enclosed.

Respectfully submitted,



William L. Warren

Reg. No. 36,714

SUTHERLAND ASBILL & BRENNAN LLP
999 Peachtree Street, NE
Atlanta, Georgia 30309-3996
(404) 853-8000
Our Docket: 18744-0029